



CUTBACKS

MEDIUM CURING CUTBACK ASPHALTS SPECIFICATION TABLE

PROPERTIES	MC-30	MC-70	MC-250	MC-800	MC-3000
Tests on Liquid Asphalt	min-max	min-max	min-max	min-max	min-max
Flash Point (TOC), °C	38 min	38 min	65 min	65 min	65 min
Kinematic Viscosity, 60°C, mm ² /s	30 - 60	70 - 140	250 - 500	800 - 1600	3000 – 6000
Distillation Test Distillate, % of total to 360°C					
to 225°C	25 max	20 max	10 max		
to 260°C	40 – 70	20 – 60	15 – 55	35 max	15 max
to 316°C	75 - 93	65 - 90	60 - 87	45 - 80	15 - 75
Residue from Distillation, 360°C, %	50 min	55 min	67 min	75 min	80 min
Tests on Residue					
Penetration, 25°C, dmm	120 - 250	120 - 250	120 - 250	120 - 250	120 - 250
Solubility in TCE, %	99.5 min	99.5 min	99.5 min	99.5 min	99.5 min
Ductility, 25°C, cm	100 min	100 min	100 min	100 min	100 min



McASPHALT INDUSTRIES LIMITED

8800 Sheppard Avenue East T 416.281.8181 TF 1.800.268.4238
 Toronto, ON M1B 5R4 F 416.281.8842 E info@mcasphalt.com

mcasphalt.com
 ISO 9001/14001/45001