



## SLOW CURING CUTBACK ASPHALTS SPECIFICATION TABLE

PROPERTIES	SC-70	SC-250	SC-800	SC-3000
<b>Tests on Liquid Asphalt</b>	<b>min-max</b>	<b>min-max</b>	<b>min-max</b>	<b>min-max</b>
Flash Point (COC), °C	65 min	80 min	90 min	105 min
Kinematic Viscosity, 60°C, mm <sup>2</sup> /s	70 - 140	250 - 500	80 - 1600	3000 - 6000
Distillation Test Distillate, % of total to 360°C	10 - 30	4 - 20	2 - 12	5 max
<b>Tests on Residue</b>				
Kinematic Viscosity, 60°C, mm <sup>2</sup> /s	4 - 70	8 - 100	20 - 160	40 - 350
Solubility in TCE, %	99.5 min	99.5 min	99.5 min	99.5 min
<b>Penetration Specific Residue Tests</b>				
Residue of 100 Penetration, %	50 min	60 min	70 min	80 min
Ductility of 100 Penetration, 25°C, cm	100 min	100 min	100 min	100 min



**McASPHALT INDUSTRIES LIMITED**

8800 Sheppard Avenue East T 416.281.8181 TF 1.800.268.4238  
Toronto, ON M1B 5R4 F 416.281.8842 E info@mcasphalt.com

mcasphalt.com  
ISO 9001/14001/45001